

			FİZİKSEL / PHYSICAL			MEKANİK / MECHANICAL				TERMAL / THERMAL		
			Akışkanlık / MFI (PP 230°C-2,16 kg) (PE 190°C-2,16 kg)	Yoğunluk/ Density 23°C	Kül / Ash	Kopma mukavemeti / Breaking Strength	Kopmada Uzama / Elongation at break	Çekme Modülü / Tensile Modulus	Charpy Notched Impact Strength (23 °C)	Nem / Moisture	Yanmazlık / Flame	Erime Noktası Melting point (DSC)
Ürün Grubu Product Group	Ürün Adı Product Name	Ürün Rengi Product Color	ISO 1133-1	ISO 1183	ISO 247	ISO 527-1/2	ISO 527-1/2	ISO 527-1/2	ISO 179-1	ISO 787-2	UL-94	ASTM D3418
			gr/10 min.	g/cm ³	%	Mpa	%	Mpa	kJ/m ²	%		°C
Metiplen 001	LDPE	LDPE Kırık Beyaz / Off White	0,4-0,6	0,930-0,950	5-10,	15-17	450-500.	700-800	0,2-0,5.	HB	105
		LDPE Gri / Grey	0,4-0,6	0,930-0,950	4-8,	15-17	450-500.	700-800	0,2-0,5.	HB	105
		LDPE Şeffaf / LDPE Transparent	0,3-0,5	0,918-0,922	0	17-18	500-600.	700-800	0,2-0,5.	HB	105
		LDPE K. Şeffaf / Dark Transparent	0,8-1,5,	0,920-0,925	0	13-15	400-450.	650-750	0,2-0,5.	HB	105
		LDPE Eco Naturel / Eco Natural	1-1,50	0,918-0,922	0	16-17	450-550	700-800	0,2-0,5.	HB	105
		LDPE Eco Siyah / Eco Black	1-1,50	0,930-0,950	4-8,	15-17	450-500.	700-800	0,2-0,5.	HB	105
	LLDPE	LLDPE Bal Köpüğü /Honey Color	2-3.	0,93-0,95	0-3.	13-15	500-600	250-300	0,2-0,5.	HB	95
Metiplen 002		HDPE Siyah / Black	1-1,5	0,93-0,95	1-4.	14-16.	400-450	650-700	0,2-0,5.	HB	130
<p>Yukarıda yazılı test sonuçları laboratuvar ortamında standartlara uygun olarak yapılmış ölçümlerden elde edilmiştir. Karar aşamasında kullanıcı kendi iç test metodlarına göre testleri tekrarlaması uygun olacaktır. Bu datasheetteki test sonuçları istatistiksel ortalama değerleri baz alınarak oluşturulmuştur. Ürün özelliklerine ve partiye göre değişiklik gösterebilmektedir.</p> <p>In writing the above laboratory test results were obtained from measurements made in accordance with the standards. The decision will be appropriate to repeat the test users according to their own internal testing method. Test results in this datasheet is established based on the statistical average value. Products and features may vary by party.</p>												